

FOREVER MULTI-TRANS

Instructions for printing onto mugs

PRINT SETTINGS	PRESS SETTINGS
Paper Weight · 140gsm	Pressure · High - 5bar (70 PSI)
Image Mode · Mirror/Reverse	Temperature · 140°C (284°F)
Feed Mode · Multi-Purpose Tray (Bypass/Manual Feed)	Time · 180 seconds

BEFORE YOU START

1. Preheat your mug press
2. Use a silicone wrap over your mug for even heat distribution (see www.forevertransferpaper.com/silicone-wrap)

APPLICATION

1. Position the transfer onto your mug and fix using heat tape (see www.forevertransferpaper.com/heat-tape)
2. Place your mug into your heat press.
3. Press for 180 seconds at 140°C (284°F).
4. Allow the mug to cool completely.
5. Remove transfer paper.

HINT · unwanted residue can be removed by rubbing with Isopropyl Alcohol wipes.

These instructions are based on using a professional heat press, adjustments may be required depending on the press you are using.

This transfer paper is not suitable for application using a household iron.

This transfer paper is suitable only for Laser Printers.

Are you experiencing problems with this transfer paper?

Don't panic, it does work.

Call us on 01244 541 647 or E-Mail info@forevertransferpaper.com

FOREVER MULTI-TRANS

see forevertransferpaper.com/multi-trans for printable materials

PRINT SETTINGS		PRESS SETTINGS	
Paper Weight · 140gsm		Pressure · See Below	
Image Mode · Mirror/Reverse		Temperature · 200°C (390°F)	
Feed Mode · Multi-Purpose Tray (Bypass/Manual Feed)		Time · See below	
SURFACE	PRESSURE	TIME	PEEL
ALUMINIUM	4-5 bar (55-70 PSI)	3 minutes	Warm or Cold
WOOD	3 bar (40 PSI)	4-5 minutes	Immediately
CERAMICS	4-5 bar (55-70 PSI)	5 minutes	Warm or Cold
MAGNETIC VINYL	4-5 bar (55-70 PSI)	3 minutes	Warm or Cold
ACRYLIC GLASS	4-5 bar (55-70 PSI)	3 minutes	Let cool for 5 - 10 seconds
MIRROR	4-5 bar (55-70 PSI)	3 minutes	Warm or Cold

APPLICATION

1. Position substrate onto your heat press
2. Position FOREVER Multi-Trans onto substrate and cover with a Rubber Mat
3. Press for the time mentioned above
4. Peel the transfer as above

To cure FOREVER Multi-Trans, swing the platen of your heat press over the finished item (DO NOT CLOSE) and simply allow the heat of your press to radiate onto the item for 2-3 minutes

Are you experiencing problems with this transfer paper?

Don't panic, it does work.

Call us on 01244 541 647 or E-Mail info@forevertransferpaper.com